



DECORATIVE WATER-BASED INTERIOR PRODUCT GROUP

BETEK GEL PRIMER

PRODUCT DESCRIPTION

A ready-to-use transparent plaster emulsion primer emulsion based on copolymer, specially developed for use in conditions where standard primers are insufficient before paint application. It prevents high absorbency of plastered surfaces.

FEATURES

- Non-drip formula
- Even distribution
- Fast and easy application
- Suitable for application on both ceilings and walls.

It forms a layer between the paint and the surface. With its high penetrating ability, it allows the finishing coat of paint to penetrate deeper into the painted surface. It prevents the paint from drying prematurely, especially in hot weather conditions, and reduces paint consumption by limiting absorption into the surface.

APPLICATION SURFACES

It is used for priming surfaces with very high absorbency and/or high dust formation, such as plastered surfaces, low-quality highly absorbent surfaces, surfaces painted with plastic paint, as well as aerated concrete surfaces, prior to the application of any type of plastic or silicone-based interior paints.

APPLICATION

The surface to be painted must be smooth, strong, and capable of withstanding the primer and finishing paint. Clean it from contaminants, dust, grease, loose paint, and repair any surface defects. Observe the required curing times for cement, concrete mixtures, and newly plastered surfaces (28 days).

Sand plastered and similar surfaces, remove the dust with a damp cloth, and apply the Betek gel primer. Painting can be carried out 4–6 hours after applying the Betek gel primer. Ensure that during application and until complete drying, the ambient and surface temperatures remain between +5°C and +30°C, and protect the surfaces from freezing. Betek gel primer should be applied using a brush or roller, avoiding scoring and sanding (apply with a roller in one direction only, once), so as not to create a smooth surface. If a smooth surface forms, sand it with sandpaper. Avoid using airless spray application.

DILUTION

Ready to use; dilution is not permitted. Diluting the product may cause it to lose its properties that prevent dripping and splattering.

BETEK BOYA VE KİMYA SANAYİ A.Ş.

Zümrütevler Mahallesi Ural Sokak No: 38 34852 Maltepe, İstanbul / Türkiye
Tel: +90 (216) 571 11 00 - Faks: +90 (216) 571 13 70 - www.betekexport.com



**DRYING TIME (at 20°C and 65% relative humidity)**

Touch dry: 20 minutes

Painting: 4–6 hours (drying time may increase with higher relative humidity and lower temperatures).

CONSUMPTION

15–20 m²/liter per single coat, depending on the type, absorbency, and texture of the surface. For an accurate consumption calculation, a test application should be performed.

STORAGE CONDITIONS

Store in a tightly closed original packaging in a cool, dry place. Protect from direct sunlight and low temperatures. Shelf life is 3 years. Close the container tightly immediately after use.

PACKAGING

15 L; 7.5 L; 2.5 L

WARNING

Caution!

HAZARD WARNINGS

H317: May cause an allergic skin reaction.

SAFETY PRECAUTIONS

P101: If medical advice is needed, have the product container or label at hand.

P102: Keep out of reach of children.

P103: Read the label before use.

P261: Avoid breathing dust/fumes/gas/mist/vapors/spray.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P321: Specific treatment (see instructions on this label).

P363: Wash contaminated clothing before reuse.

P333 + P313: If skin irritation or rash occurs: Get medical advice/attention.

P501: Dispose of contents/container in accordance with local, regional, national, and international regulations.

This technical data sheet has been prepared based on laboratory data obtained under normal conditions. For additional information, please contact the technical personnel. Otherwise, the manufacturer shall not be held responsible for unsatisfactory results arising from insufficient information. Our company reserves the right to modify this information.

For further details regarding safe handling, health and safety risks, and precautionary measures related to the product, please refer to the Material Safety Data Sheets (MSDS).

This material is produced by Betek A.Ş., a company certified in compliance with the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, and TS ISO/IEC 27001.

Edition 0, January 19

BETEK BOYA VE KİMYA SANAYİ A.Ş.

Zümrütevler Mahallesi Ural Sokak No: 38 34852 Maltepe, İstanbul / Türkiye
Tel: +90 (216) 571 11 00 - Faks: +90 (216) 571 13 70 - www.betekexport.com

